

A Review Article: Composite Preheating



Amirreza Hendi ¹, Mehran Falahchai ¹, Donya Maleki ², Dina Maleki ^{2*}

¹ Dental Sciences Research Center, Department of Prosthodontics, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran

² Dental Student, Student Research Committee, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran

Use your device to scan
and read the article online



Citation: Hendi A, Falahchai M, Maleki D, Maleki D. Composite Preheating. Journal of Dentomaxillofacial Radiology, Pathology and Surgery. 2019; 8(1):37-40. <http://dx.doi.org/10.32598/3dj.7.4.145>

<http://3dj.gums.ac.ir>



ABSTRACT

The aim of this study is to evaluate the effect of preheating on composite resins' mechanical and physical properties. Preheating of composite resins positively affects the degree of conversion, viscosity, microleakage, marginal adaptation, microhardness and color change however, the flexural strength is adversely affected.

Article info:

Received: 2019/03/08

Accepted: 2019/03/19

Keywords:

Composite Resins
Flexural Strength

* Corresponding Author:

Dina Maleki .

Address: School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran.

Tel: +989128998663

E-mail: Dinamaleki74@gmail.com

Introduction:

Nowadays composite resins are highly recommended as restorative materials due to underwhelming mechanical and aesthetic properties and as a mercury-free alternative material to amalgam. (1) Polymerization shrinkage, postoperative sensitivity, inadequate proximal contact, poor wear resistance and lack of proper adaptation in some clinical conditions are composite resins' drawbacks. (2)

Preheating was first introduced by Friedman in 2001. (3) Increment of restoration durability and stress relief (2,4), better adaptation (5) and shortening of curing time (6) are the benefits of preheating used to improve mechanical properties of composite resins. However, Daronch et al. reported no significant difference between the preheated composite resins and composite resins. (7) Decreasing shelf life and requiring quick work are the drawbacks of composite preheating. (8) Also, pulp compatibility is of concern when composite resins are preheated to 54-68°C. Nevertheless, studies have found that pulp temperature is raised only by 0.8°C after placement of a 60°C preheated composite resin while 20s of light curing increases pulp temperature by 5°C. (9) Daronch et al. found that after removing composites from heating device, 50% of the temperature attained will be lost after 2 minutes and almost 90% will be lost after 5 minutes. (7)

Microleakage and preheating

Poor marginal adaptation and composite shrinkage causes micro leakage and consequently, results in recurrent caries, food retention and even restoration failure. (10) There were attempts to improve adaptation and to limit shrinkage of composite resins.

At first, the researchers added filler to resin composites to improve the adaptation. (10) Yet, increasing the filler load resulted in higher viscosity which led to concerns about handling of the resin composite material and could leave behind unwanted void (11)

A variety of studies have shown that lower viscosity composites can improve adaptation

and reduce microleakage. (12-15) In this regard, researchers introduced flowable composites by decreasing the filler load. (11) However, the flowable composites were not as durable and resistant as higher viscosity resin composites which restricted their application in restoration of posterior teeth. (11-16) Preheating resin composite was an approach to mimic flowable composites in achieving better adaptability by reducing viscosity, without losing its mechanical properties. (10) The findings of Holmes et al., Broome et al., Blalock et al., Wanger et al., Salgado et al. and Yang et al. support the benefits of preheating in decreasing microleakage of resin composite restorations. (3,9,15,17-19)

Preheating of resin composites, besides decreasing microleakage by increasing flowability and adaptation, leads to a more homogeneous polymerization and subsequently to a more homogeneous shrinkage and reduces the micro leakage. (20)

Preheating and mechanical properties

Degree of conversion is defined as the ratio of the remaining C=C double bonds in a cured resin composite to the total number of C=C bonds in the uncured material. (8-9) Degree of conversion is a parameter to determine final mechanical properties of restorative materials. (9) In other words, a lower degree of conversion decreases composite resins' microhardness, wear resistance, fracture resistance and flexural strength. (9-11)

Studies suggest preheating of composite resins as a method to enhance degree of conversion and subsequently, to enhance microhardness, wear resistance and fracture resistance, by increasing temperature. (12,14-18) Increment of temperature leads to further mobility of monomers and better cross-linked polymerized networks. (1,9) The idea of improving mechanical properties of resin composites by preheating is confirmed by Torres et al., Kashi et al., Eman et al. and Lucy et al. (21-24). On the contrary, Didron et al (20) found that preheating to have no significant effect on microhardness. Degree of conversion

may vary based on the brand and the shade of the composite resin which explain the different findings of above-mentioned studies. (3)

Flexural strength is a critical parameter for brittle materials and is correlated to the degree of conversion. (3-6) Although, pre-heating of composite resins increases degree of conversion, it has no significant effect on flexural strength. (3) Salgado et al, Nada et al. and Uctasli et al. no significant difference in flexural strength between preheated and non-heated composites. (3,25,26) Even, Amario et al, reported that highly repeated cycles of preheating may have negative effects on the flexural strength of resin composites. (27)

Color stability

According to Micali and Basting residual monomers in the polymeric chain can form colorimetric degradation products. (28) On the other side, non-converted double carbon link can increase the penetration of solvent from oral cavity and hydrolyze the silane around filler which creates microcracks and make the resin composite more susceptible to discoloration. (29) Also, microleakage leads to penetration of extrinsic staining into the restoration. (19,30-31)

As previously discussed, preheating composite can lead to better color stability by increasing degree of conversion and marginal adaptation which decrease residual monomers, non-converted double carbon link and microleakage, consequently. This claim is verified by Tomaselli et al., Mundim et al. and Kahnamouei et al. (32-34)

Conclusion

It is concluded that preheating of composite resins positively affects the degree of conversion, viscosity, microleakage, marginal adaptation, microhardness and color change however, the flexural strength is adversely affected.

However, in order to assess the clinical significance of pre-heating, further studies with larger sample size and analogous experimental conditions are required.

References

1. Theobaldo JD, Aguiar FHB, Pini NIP, Lima DANL, Liporoni PCS, Catelan A. Effect Of Preheating And Light-Curing Unit On Physicochemical Properties Of A Bulk Fill Composite. *Clin Cosmet Investig Dent*. 2017;9(2):39-43 <https://doi.org/10.2147/CCIDE.S130803>
2. Mohammadi N, Jafari-Navimipour E, Kimyai S, Et Al. Effect Of Pre-Heating On The Mechanical Properties Of Silorane-Based And Methacrylate-Based Composites. *J Clin Exp Dent*. 2016;8(4):E373-E378 <https://doi.org/10.4317/Jced.52807>
3. Froes-Salgado NR, Silva LM, Kawano Y, Francci C, Reis A, & Loguercio AD . Composite Pre-Heating: Effects On Marginal Adaptation, Degree Of Conversion And Mechanical Properties *Dental Materials*, 2010;26(9): 908-914. <https://doi.org/10.1016/j.dental.2010.03.023>
4. Garoushi, S., Vallittu, P., Shinya, A. Et Al. Influence Of Increment Thickness On Light Transmission, Degree Of Conversion And Micro Hardness Of Bulk Fill Composites. *Odontology*, 2016; 104(1): 291-8 <https://doi.org/10.1007/s10266-015-0227-0>
5. D'Amario M, Pacioni S, Capogreco M, Gatto R, & Baldi M .Effect Of Repeated Preheating Cycles On Flexural Strength Of Resin Composites *Operative Dentistry*. 2013; 38(1): 33-38 <https://doi.org/10.2341/11-476-L>
6. Jafarzadeh-Kashi TS, Mirzaii M, Erfan M, Fazel A, Eskandarion S, Rakhshan V. Polymerization Behavior And Thermal Characteristics Of Two New Composites At Five Temperatures: Refrigeration To Preheating. *J Adv Prosthodont*. 2011;3(4):216-220 <https://doi.org/10.4047/jap.2011.3.4.216>
7. Daronch M., Rueggeberg F.A., Hall G., De Goes M.F. Effect Of Composite Temperature On In Vitro Intrapulpal Temperature Rise. *Dent. Mater*. 2007;23(1):1283-1288 <https://doi.org/10.1016/j.dental.2006.11.024>
8. Galvão MR, Caldas SG, Bagnato VS, De Souza Rastelli AN, De Andrade MF. Evaluation Of Degree Of Conversion And Hardness Of Dental Composites Photo-Activated With Different Light Guide Tips. *Eur J Dent*. 2013;7(1):86-93.
9. Yang JN, Raj JD, Sherlin H. Effects Of Preheated Composite On Micro Leakage-An In-Vitro Study. *J Clin Diagn Res*. 2016;10(6):ZC36-ZC38 <https://doi.org/10.7860/JCDR/2016/18084.7980>
10. Karaarslan ES, Usumez A, Ozturk B, Cebe MA. Effect Of Cavity Preparation Techniques And Different Preheating Procedures On Microleakage Of Class V Resin Restorations. *Eur J Dent*. 2012;6(1):87-94. <https://doi.org/10.1055/s-0039-1698935>
11. Zhao S, Qian Y, Liu H, Jiang L, Zhou L. The Effect Of Preheating On Light Cured Resin Composites. *J Hard Tissue Biol* 2012;21(3):273-8. <https://doi.org/10.2485/>

jhtb.21.273

12. Opdam NJM, Roeters JJM, Joosten M & Veeke OV . Porosities And Voids In Class I Restorations Placed By Six Operators Using A Packable Or Syringable Composite Dental Materials,2002; 18(1): 58-63.[https://doi.org/10.1016/S0109-5641\(01\)00020-3](https://doi.org/10.1016/S0109-5641(01)00020-3)
13. Unlu N, Krakaya S, Ozer F & Say EC . Reducing Microleakage In Composite Resin Restorations: An In Vitro Study European Journal Of Prosthodontic Restorative Dentistry.2003; 11(4): 171-175.
14. Bayne SC, Thompson JY, Swift EJ Jr, Stamatides P & Wilkerson M .A Characterization Of First-Generation Flowable Composites Journal Of The American Dental Association,1998; 129(5): 567-77.<https://doi.org/10.14219/jada.archive.1998.0274>
15. Blalock JS, Holmes RG & Rueggeberg FA . Effect Of Temperature On Unpolymerized Composite Resin Film Thickness Journal Of Prosthetic Dentistry .2006;96(6): 424-432.<https://doi.org/10.1016/j.prosdent.2006.09.022>
16. Didron PP, Chrzanowski W, Ellakwa A. Effect Of Temperatures On Polymerization Stress And Microleakage Of Class V Composite Restorations. Open Journal Of Composite Materials,2003;3(3): 107-112.<https://doi.org/10.4236/ojcm.2013.34011>
17. Holmes RG, Blalock JS, Rueggeberg FA. Composite film thickness at various temperatures. J Dent Res. 2004;83(2):32-65.
18. Broome JC. Effects of preheating resin composite on flowability. The Dental Advisor. 2006;4(1):4-9.
19. Wagner WC, Aksu MN, Neme AM, Linger JB, Pink FE, Walker S. Effect Of Pre-Heating Resin Composite On Restoration Microleakage. Oper Dent.2008 ;33(2):72-8<https://doi.org/10.2341/07-41>
20. Didron PP, Ellakwa A, Swain MV. Effect of pre-heat temperatures on mechanical properties and polymerization contraction stress of dental composites. Materials Sciences and Applications,2013;4(6):12-9
21. Torres CRG, Caneppele TMF, Borges AB, Torres ACM, Araujo MAM. Influence Of Precure Temperature On Vickers Microhardness Of Resin Composite. Int J Contemp Dent. 2011; 2(1): 41-5.
22. Eman M, Ibrahim L, Adel A, Kamar A.Effect of oreheating on Microleakage and microhardness of composite resin(an in vitro study).Alexandria Dental Journal. 2016;41(1):4-11.<https://doi.org/10.21608/adjalexu.2016.59163>
23. Jafarzadeh-Kashi TS, Fereidouni F, Khoshroo K, Heidari S, Masaeli R, Mohammadian M. Effect Of Preheating On The Microhardness Of Nanohybrid Resin-Based Composites. Frontiers In Biomedical Technologies. 2015;2(1):15-22.
24. Lucey S, Lynch C, Ray N, Burke F, Hannigan A. Effect Of Pre-Heating On The Viscosity And Microhardness Of A Resin Composite. J Oral Rehabil. 2010;37(1):278-82.<https://doi.org/10.1111/j.1365-2842.2009.02045.x>
25. Nada K, El-Mowafy O. Effect Of Precuring Warming On Mechanical Properties Of Restorative Composites. Int J Dent. 2011;20(11):45-9<https://doi.org/10.1155/2011/536212>
26. Uctasli MB, Arisu HD, Lasilla LV, Valittu PK. Effect Of Preheating On The Mechanical Properties Of Resin Composites. Eur J Dent. 2008;2(6):263-8.<https://doi.org/10.1055/s-0039-1697390>
27. D'amario M, Pacioni S, Capogreco M, Gatto R, Baldi M. Effect Of Repeated Preheating Cycles On Flexural Strength Of Resin Composites. Operative Dentistry. 2013;38(1):33-8.<https://doi.org/10.2341/11-476-L>
28. Micali B, Basting RT. Effectiveness Of Composite Resin Polymerization Using Light-Emitting Diodes (Leds) Or Halogen-Based Light-Curing Units. Brazilian Oral Research 2004;18(4):266-70.<https://doi.org/10.1590/S1806-83242004000300016>
29. Sousa SE, Da Costa ES, Borges BC, De Assunção IV, Dos Santos AJ. Staining Resistance Of Preheated Flowable Composites To Drinking Pigmented Beverages. Revista Portuguesa De Estomatologia, Medicina Dentária E Cirurgia Maxilofacial. 2015;56(4):221-5. <https://doi.org/10.1016/j.rpemd.2015.11.009>
30. Um CM, Ruyter IE. Staining Of Resin-Based Veneering Materials With Coffee And Tea.Quintessence Int.1991;22(4):377- 386.
31. Daronch M, Rueggeberg FA, De Goes MF .Monomer Conversion Of Pre-Heated Composite.J Dental Res, 2005;84(1):663-7<https://doi.org/10.1177/154405910508400716>
32. Tomaselli LD, Oliveira DC, Favarão J, Silva AF, Pires-de-Souza FD, Geraldeli S, Sinhoreti MA. Influence of Pre-Heating Regular Resin Composites and Flowable Composites on Luting Ceramic Veneers with Different Thicknesses. Brazilian dental journal. 2019 Oct;30(5):459-66<https://doi.org/10.1590/0103-6440201902513>
33. Mundim FM, Garcia LD, Cruvinel DR, Lima FA, Bachmann L, Pires-De FD. Color Stability, Opacity And Degree Of Conversion Of Pre-Heated Composites. Journal Of Dentistry. 2011;39(5):E25-9.<https://doi.org/10.1016/j.jdent.2010.12.001>
34. Kahn mouei MA, Gholizadeh S, Rikhtegaran S, Daneshpooy M, Kimyai S, Oskoe PA, Rezaei Y. Effect Of Preheat Repetition On Color Stability Of Methacrylate-And Silorane-Based Composite Resins. Journal Of Dental Research, Dental Clinics, Dental Prospects. 2017;11(4):222-229