

Review Paper: Different ways to measure marginal fit and internal adaptation of restorations in dentistry



Mehrsima Ghavami-Lahiji¹ , Mehran Falahchai^{2*} , Abolfazl Habibi Arbastan³ 

¹Department of Restorative Dentistry, Dental Sciences Research Center, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran.

²Department of Prosthodontics, Dental Sciences Research Center, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran.

³School of Dentistry, Guilan University of Medical Sciences, Anzali International Campus, Bandar Anzali, Iran.

Use your device to scan
and read the article online



Citation: Ghavami-Lahiji M, Falahchai M, Habibi Arbastan A. Different ways to measure marginal fit and internal adaptation of restorations in dentistry. Journal of Dentomaxillofacial Radiology, Pathology and Surgery. 2023; 12(1):18-26. <http://dx.doi.org>

<http://3dj.gums.ac.ir>



ABSTRACT

The purpose of this review article was to summarize the scientific literature investigating all invitro methods that can evaluate both marginal and internal adaptation of direct and indirect restorations. An electronic search of publications from 2000 to March 2022 was made using ScienceDirect, PubMed, and Google Scholar databases. The search included only English-language articles. Therefore, only studies that addressed techniques to measure marginal and internal adaptation in different restorations were selected. Five laboratory methods with different capabilities have been introduced to check the adaptation of dental restorations, including sectioning, Silicon Replica Technique (SRT), Micro-CT, OCT, and triple scan method. In addition, there are factors that may contribute to differences between different methods in measuring adaptation, including 2D, 3D, and absolute adaptation, cost, and feasibility of performing in the oral cavity. SRT and traditional sectioning have the advantage of being simple and inexpensive procedures. Micro-CT, OCT, and triple scan method are costly procedures that necessitate specialized equipment and analysis software which enable both 2D and 3D analysis. Another crucial aspect of the assessment techniques to be applied in clinical trials is the capability to conduct an examination in the oral cavity. Sectioning, OCT, and Micro-CT cannot be used to make assessments in the oral cavity, however SRT and triple scan method can. The search for an ideal and standardized device to measure the adaptation of direct and indirect restorations in dentistry is still needed.

Article info

Received: 2022/10/06

Accepted: 2022/12/31

Keywords:

Dental Marginal
Adaptation, Dental
Internal Adaptations,
Permanent Dental
Restorations

* Corresponding Author:

Mehran Falahchai

Address: Department of Prosthodontics,
School of Dentistry, Guilan University of
Medical Sciences, Rasht-Fooman Road,
Rasht, Iran.

Tel: +98 - 1333486406

E-mail: mehran.falahchai@gmail.com

Introduction

The clinical success of dental restorations is determined by three main factors including esthetics, fracture strength, and adaptation of the restoration to tooth structure. Marginal and internal fit play a vital role for long-term clinical success both direct and indirect dental restorations using composites, ceramics, and crowns. (1) Resin composite restorations are a common choice among clinicians due to rising demand for aesthetics and advancements in adhesive system technology. (2) However, a significant problem in clinical practice is shrinkage related to the polymerization of materials. When shrinkage stress exceeds the bond strength of the adhesive interface or the cohesive strength of the tooth, the interfacial quality of the restoration is negatively affected, leading to gap formation. Polymerization shrinkage, which is an intrinsic property of resin composites and is directly related to their composition, appears to be responsible for the poor fit of resin composite restorations. Modifications to the material composition have been made by various manufacturers to reduce the effects of polymerization shrinkage and the internal/marginal gap formation. (3)

Furthermore, it has been reported that mechanical properties of resin-based materials can be reduced by defects such as voids, gaps, and bubbles. Although the structural properties of the restorative material may initially be appropriate, defects can reduce the performance of the restorations under fatigue load and decline the durability of the restorative material, leading to fractures and clinical failure. The viscosity of the material, the size of the applicator tip, the entrapment of air inside the bulk of composite resin during the manufacturing process, as well as the incremental technique and other placement techniques can all cause void formation in the material bulk or cavity walls. (4, 5)

In the spaces between cavity walls and the restorative material, polymerization shrinkage stress allows fluid movement and bacterial infiltration. (6) Microleakage, which is defined as clinically undetectable penetration, can cause

pulpal inflammation and necrosis, secondary caries, post-operative hypersensitivity, marginal staining, and post-operative hypersensitivity. (2) Microleakage can happen inside the tooth or on its external surface. Hypersensitivity to the cold or pain when chewing can be the result of poor internal adaptation. (7)

Indirect restorations are similarly subject to the aforementioned problems. The quality of marginal adaptation and internal adaptation are two elements that influence durability of an indirect restoration. Microleakage, luting cement dissolution, secondary caries, and gingival irritation can all be consequences of poor marginal adaptation.

Poorly adapted restorations are supported by cement, which has an impact on the restoration's lifespan because it is weaker than the tooth structure. Consequently, ceramic restorations like inlay restorations should have a homogeneous internal fit. Additionally, a poor internal fit not only can lead to an increase in cement thickness but also change retention, influence occlusion, lessen the restorations' resistance to fracture and compromise the marginal fit. Since inlay/Onlay restorations' margins are subject to mechanical, physical, and thermal stresses, internal and marginal adaptability are especially crucial. (8-10) .

Since incorrect interpretation of the marginal and internal fit assessments could lead to incorrect marginal fit values, maintaining patients' long-term health can be challenging. As a result, a Comprehensive technique for assessing the marginal and internal fit of direct and indirect restorations is required. Therefore, the aim of this study was to review in vitro studies in terms of different techniques which can evaluate both marginal and internal adaptation of direct and indirect restorations.

Materials and Methods

An electronic search of publications from 2000 to March 2022 was made using ScienceDirect, PubMed, and Google Scholar databases. The search included only English-language

articles. Therefore, only studies that addressed techniques to measure marginal and internal adaptation in different restorations were selected.

Five laboratory methods with different capabilities have been introduced in the literature to evaluate the fitness of dental restorations, including sectioning, Silicon Replica Technique (SRT), Micro-CT, OCT, and triple scan method.

Traditional sectioning (Cross-sectional method)

One of the traditional methods that have been used to analyze the internal adaptation caused by polymer shrinkage were dye and tracer penetration methods.(11, 12) These methods demand soaking the specimens in various solutions, cutting sections through the restorations, and examining the leakage that has occurred under a light microscope. Tracers that can be utilized for infiltration include methylene blue, rhodamine, erythrosine, and silver nitrate. Although the specimens must be sliced to be studied, these processes are relatively straightforward. Dye

samples cannot be reevaluated; they can only be evaluated on the plane on which they were sectioned. After cutting specimens into sections, the resin-dentin interface can also be examined by Scanning Electron Microscopy (SEM). This method has limitations in quantitative evaluation and is particularly technique sensitive.(13, 14) Additionally, internal adaptation before and after thermomechanical loading cannot be compared using conventional techniques, which need sectioning and dye penetration. The other drawback is inability to take measurements inside the oral cavity.(7)

The cross-sectional method has also been employed for indirect restorations. With this method, the desired portion of the prosthesis is cut and measured with an optical or electronic microscope after cementation. It has the benefit of permitting precise measurement of the internal and marginal fit of the prosthesis because the actual prosthesis is cut and measured.(15, 16) Information on the contents of the related articles is summarized in Table 1.

Table 1. Application of different techniques for measuring adaptation of restorations in recent studies

Article	Type of measurement/technique	restoration	Result
Stavridakis et al. 2007(11)	Sectioning for internal analysis + SEM polyvinylsiloxane impression material on a polished restoration for marginal analysis + SEM	Different adhesive restorative system in different cavity designs.	In large posterior cavities, the C-factor significantly affects internal and marginal adaptation.
Dionysopoulos et al. 2014(12)	Sectioning for internal analysis + SEM internal gap on axial wall	Different restorative techniques in cl V cavity designs.	Following photopolymerization, different restorative techniques behave differently in terms of internal adaptability to dentin.
Rajan et al. 2015(16)	Sectioning longitudinally + stereomicroscope analyzing using ImageScope software	zirconia copings fabricated by two CAD/CAM systems	Internal adaptation and marginal fit were demonstrated by both CAD/CAM system copings within an acceptable discrepancy range.
Falahchai et al. 2021(21)	SRT	Endocrowns fabricated with zirconia using digital scans and conventional impression	Both the traditional impression technique and the digital scanning technique produced crowns with similar marginal adaptation.
Falahchai et al. 2021(23)	SRT	Provisional Restoration Fabricated With Additive, Subtractive, And Conventional Techniques	FDPs fabricated digitally had a superior marginal fit and higher fracture resistance than conventionally fabricated ones.

Article	Type of measurement/ technique	restoration	Result
Sarda et al.2021(41)	SRT	Cobalt Chromium Restorations	Compared with milled wax/lost wax methods, DMLS techniques produced significantly better marginal fit for cobalt-chromium alloy copings
Özal et al.2021(42)	SRT	Restorations fabricated with monolithic zirconia using digital scans	Intraoral scanners generally had lower marginal and internal discrepancies than laboratory scanners
Gautam et al.2021(43)	SRT	Cobalt–Chromium (Co–Cr) Copings	In contrast to conventional cast Co–Cr alloy crowns, the marginal gap for copings made using direct metal laser-sintered crowns was lesser.
Mansour et al.2021(44)	SRT	Ceramometallic restoration (cad wax and press veneering)	Microleakage of ceramometallic restorations is strongly correlated with internal fit.
Son et al.2021(29)	Triple scan	Ceramic crowns fabricated with chairside cad/cam systems	All three chairside CAD/CAM systems produced clinically acceptable prostheses. The marginal gap, which is the most important element in the marginal and internal fit of prostheses, was recorded to be below 100 µm for each all three systems.
Holst et al. 2011(30)	Triple scan	Titanium single crown copings fabricated with CAD/CAM systems	The triple-scan protocol is an effective surface data set registration method for dental applications and removes the restrictions of traditional best-fit registration protocols in the case of cement space or gap
Haak et al. 2021(32)	OCT	Ceramic veneers (IPS InLine Veneer) of two thicknesses in different preparation design	The interfacial bond benefits from a ceramic thickness of at least 0.5 mm and a preparation that does not expose dentine.
Han et al. 2016(18)	OCT & Micro-CT	Different adhesive restorative system in cylindrical cavities	Although the measured imperfective margins% in micro-CT differed from those in SS-OCT, there was a fair amount of correlation between the two techniques.
Han et al. 2014(7)	Micro-CT	Different adhesive restorative system in cl I cavities	Following thermomechanical load cycling, the groups using various adhesive systems showed variations in internal adaptation.
Ashiry 2019(36)	Micro-CT	Direct restoration of cl V cavities with and without liner	using Biodentine as liner under cl V cavities exhibited a higher internal adaptation.
Topkara et al. 2021(35)	Micro-CT	Endocrown CEREC Blocs	The amount of Internal and marginal adaptation of endocrowns was different between mandibular and maxillary and molars
Bayrak et al.2020(34)	Micro-CT	Felspathic inlays fabricated by different software programs	marginal and internal fit of inlays designed with different software programs were statistically different.

There are limited studies that carry out an objective comparison of different techniques of assessment.(15, 17, 18) However, Son et al,

performed five internal and marginal fit evaluation methods for fixed prostheses. They found except for the angle region the Silicon Replica

Technique (SRT) showed the most approximate value to the cross-sectional method. Based on their findings, it was not found significantly differences between Cross-sectional method and SRT in some points. They both demonstrated the highest values for axial region, and lowest value for margin region. However, other studied methods showed the lower values and did not show statistically significant differences in the axial region.(15)

Silicon replica technique

The same process used for cementing a prosthesis is used for the SRT. However, the procedure duplicates the internal and marginal fit for measurement while injecting silicone rather than cement into the prosthetic.(15, 19)SRT is a reliable, nondestructive method that has produced discrepancy measurements that are comparable to those of conventional cementation .(20) It has been used in numerous studies since it is a reasonably easy and inexpensive technology that enables measurements to be taken right inside the oral cavity. Furthermore, SRT can only conduct assessments utilizing two-dimensional (2D) analysis.(15)

This technique entails cutting the silicone duplicate and injecting silicone into the indirect restorations, including inlay, onlay, full crown, endocrown,(21) and interim and provisional restorations.(22, 23). After adjusting the indirect restoration to the study model and filling it with a light-body silicone, a pressure in the range of 10 to 50 N is applied to the restoration using a universal testing machine.(15, 22, 24-27)After the light-body silicone has fully polymerized, the excess is removed, and the restoration is removed leaving a thin film of light-body silicone adhering to the master tooth. Then, a medium or heavy-body silicone with a contrasting color is added to the light-body silicone to support it. The silicone is cut using a razor blade. High-magnification images are recorded with a stereomicroscope or video microscope to calculate the gaps.(15)

SRT approach is a well-established and commonly applied technique in fit investigation studies. Nevertheless, SRT comes with inherent

errors linked to challenges locating the indirect restoration margin, ripping of the elastomeric film during restoration removal from the preparation, the presence of silicone film flaws, and mistakes in the sectioning planes. Homsy et al. proposed a technique to standardize the load applied for inlay placing on the master preparation, producing replicas free from defects.(20) It is thought that the adoption of the cast index probably decreased errors caused by inadequate sectioning process management. In addition, the number of cutting directions and measuring points varies among different studies.(28)

Digital scanning

The triple scan method is a procedure that involves scanning the inside and outside of the prosthesis, the abutment tooth, and the prosthesis during the try-in stage to collect three-dimensional (3D) data and measure the marginal and internal fit by superimposing the 3D data on analysis software. It is a non-destructive, non-radioactive method that can scan the data and deliver reproducible whenever needed. But because of possible inaccuracy or overlapping of the scanned data, miscalculations might occur.(15, 29, 30)

The triple-scan method is performed in the following sequence: The inner side of the prostheses, the abutment teeth themselves (or a model thereof), those prostheses that are properly positioned on the abutment teeth are all scanned first. The spacing between the prosthetic teeth and the abutment teeth is then measured after the triple-scan data are superimposed using a best-fit alignment. This non-invasive technique enables the observation of numerous cross sections without any restrictions on direction or quantity. Researchers are also able to analyze the 3D space using this method. Additionally, it can check the prosthetics' marginal and internal fit before intraoral installation, which could enhance quality control.(29, 30) Park et al. evaluated three different fabrication methods of dental restorations using triple-scan method and SRT and reported that although triple-scan method and SRT and measurements of the occlusal region were significantly different,

no significant differences were found for other regions. Therefore, both measurement methods can be used as methods of verifying marginal and internal consistency.(17)

Optical coherence tomography (OCT)

OCT was first introduced as a non-invasive cross-sectional imaging approach for biological systems. It allows for real-time viewing of the restoration or tissue without exposing the patient to X-ray radiation. OCT is a measurement technique that employs higher resolution 2D or 3D pictures in optical scattering media using coherent light. Following the projection of a laser source over a surface, the backscattered light is converted into a signal intensity that can be shown as an image. OCT is based on light's coherent characteristics. The interference of light reflections from the reference mirror and backscattered light from the tissue generates the OCT signal. It displays cross-sectional images based on the depth resolution of the optical reflectance property.(15, 18)

OCT is a non-invasive technique that can be used for a variety of applications, including detecting dental cavities or cracks. A swept-source optical coherence tomography is a form of OCT (SS-OCT). The use of a wavelength-tuned laser as the light source improves picture resolution and scanning speed in SS-OCT.

It is important to highlight that OCT imaging depth is limited to less than 3mm of tissue. The OCT equipment was used to analyze the cavity floor in order to assess internal adaptation. Interfacial micro-gaps are visible as bright spots or lines with high signal intensity on OCT images.(31) In the picture, the change in signal intensity near the interface appears as a white cluster. A part of the light is reflected as it passes through the interface between two media with different refractive indices. This is regarded as the Fresnel phenomenon, and it is affected by the incidence angle and refractive index (n) for example, the latter is different between air, composite resin, and water.(18, 32)

Han et al. performed a comparative study to investigate the internal adaptation of resin composite restorations using two methods and

reported SS-OCT and micro-CT methods can be useful for the non-destructive assessment of internal fit. Imperfective margins measured on micro-CT showed different values than SS-OCT values, however, the two methods had a relatively high correlation.(18)

Micro computed tomography (micro-CT)

Micro-computed tomography (micro-CT) has been utilized more and more recently in restorative and prosthetic dentistry, particularly to evaluate adaptation of restorations. Compared to other methods, the micro-CT approach is considerably more expensive, but it is a non-destructive procedure. Without causing any damage to the sample, this 3D high-resolution imaging equipment delivers extensive information during the assessment of the adaptation between the restoration and tooth.(1, 10, 33-37)

A 90–150 kVA X-ray tube, filter, and collimator, a computer-controlled electric motor, a CCD camera for converting X-ray image data, an image intensifier apparatus, a specimen stand, and a computer are all necessary parts of micro-CT equipment. In vivo and ex vivo scans are the two primary varieties of micro-CT scans. For in vivo scans, an object is positioned on a stationary platform with an X-ray tube and optical X-ray detector rotating around it. In contrast, an object is put on a rotating platform for ex vivo scanning while the X-ray tube and optical X-ray detector are fixed in place. Although rotating object scanners create images with a very high resolution, they are not technically suited for imaging small animals.(38, 39)

When compared to other techniques, micro-CT has a lot of benefits, but it also has significant limitations. Due to their narrow, monochromatic X-ray and appropriate high flux, these systems have the benefit of making detailed research of X-ray imaging modality easier. The micro-CT has a nondestructive approach in contrast to microscopic approaches; the internal characteristics of the same sample can be checked multiple times, and samples stay intact for additional biological and mechanical testing. The ability to perform several scans and manage the image using specific software is an-

other advantage of micro-CT. The preparation of samples is not a challenge when this method is used instead of more damaging techniques. A more accurate measurement is made possible by overall benefits.

Micro-CT has some drawbacks, including prolonged scanning and reconstruction processing times, expensive costs, and the need for computer knowledge. The size of the image files is huge (around 3 GB). When it comes to storing and retrieving massive numbers of files, data collecting can be a challenge. The radiation dose from a micro-CT scan is sufficient to alter the immune response and other biological processes, which in turn affects the results of experiments. However, it is important to remember that they are typically not deadly. Its usage in clinical settings is restricted by the accompanying high radiation dose.(39, 40)

According to researchers, non-standardization of the sectional areas because of non-standardization of the system's samples could have an impact on the statistical findings. In indirect restorations, measurements of the same points after they have been standardized may be intriguing and significant.(34)

Conclusion

Each method for evaluating the adaptation of direct and indirect restorations that was given in this study has benefits and drawbacks. Micro-CT, OCT, and triple scan method are costly procedures that necessitate specialized equipment and analysis software. These three methods enable both 2D and 3D analysis. On the other hand, Silicon Replica Technique (SRT) and traditional sectioning have the advantage of being simple and inexpensive procedures. Another crucial aspect of the assessment techniques to be applied in clinical trials is the capability to conduct an examination in the oral cavity. sectioning, OCT, and Micro-CT cannot be used to make assessments in the oral cavity, however SRT and triple scan method can.

OCT provides the advantage of obtaining a 3D image in real time, but because of its optical

properties, no thick or opaque restorations can be used. However, because OCT is a non-radiological approach, it can be developed for use as an intra-oral probe.

Furthermore, the assessment methodologies utilized in various studies may differ based on the laboratory environment and equipment. Furthermore, there is no standard technique for determining the adaptation of dental restorations which necessitates further research in this area.

Acknowledgement

Part of the research reported in this paper was supported by Guilan University of Medical Sciences under grant number IR.GUMS.REC.1401.438.

Authors' contributions

Mehrsima Ghavami-Lahiji: Conceptualization, Methodology, Writing - Review & Editing
Mehran Falahchai: Writing - Original Draft, Data Curation, Supervision
Abolfazl Habibi Arbastan: Resources, Investigation, Visualization

Conflict of interest

The authors declare no conflict of interest

Ethical declarations

Not applicable

Financial support

None

Availability of data and material

The datasets used and/or analyzed during the current study are available from the corresponding author on reasonable request.

References

1. Akat B, Şentürk A, Ocak M, Kiliçarslan MA, Özcan M. Does cad software affect the marginal and internal fit of milled full ceramic crowns? Brazilian oral research. 2022;36:e042.<https://doi.org/10.1590/1807-3107bor-2022.vol36.0042>
2. Oğlakci B, Kazak M, Donmez N, Dalkilic EE, Koymen SS. The use of a liner under different bulk-fill resin composites: 3D GAP formation analysis by x-ray microcomputed tomography. Journal of applied oral science : revista FOB. 2020;28:e20190042.<https://doi.org/10.1590/1678-7757-2019-0042>
3. Cobb DS, MacGregor KM, Vargas MA, Denehy

- GE. The physical properties of packable and conventional posterior resin-based composites: a comparison. *Journal of the American Dental Association*. 2000;131(11):1610-5. <https://doi.org/10.14219/jada.archive.2000.0091>
4. Demirel G, Baltacıoğlu İH, Kolsuz ME, Ocak M, Orhan K. Micro-computed tomography evaluation of internal void formation of bulk-fill resin composites in Class II restorations. *Polymer Composites*. 2019;40(8):2984-92. <https://doi.org/10.1002/pc.25140>
 5. Kim YS, Baek SH, Kim RJY. Effect of vibration during bulk and incremental filling on adaptation of a bulk-fill composite resin. *Scientific reports*. 2022;12(1):21652. <https://doi.org/10.1038/s41598-022-26197-9>
 6. Araujo Fde O, Vieira LC, Monteiro Junior S. Influence of resin composite shade and location of the gingival margin on the microleakage of posterior restorations. *Operative dentistry*. 2006;31(5):556-61. <https://doi.org/10.2341/05-94>
 7. Han SH, Park SH. Micro-CT evaluation of internal adaptation in resin fillings with different dentin adhesives. *Restorative dentistry & endodontics*. 2014;39(1):24-31. <https://doi.org/10.5395/rde.2014.39.1.24>
 8. Goujat A, Abouelleil H, Colon P, Jeannin C, Pradelle N, Seux D, et al. Marginal and internal fit of CAD-CAM inlay/onlay restorations: A systematic review of in vitro studies. *The Journal of prosthetic dentistry*. 2019;121(4):590-7. <https://doi.org/10.1016/j.prosdent.2018.06.006>
 9. Kim DY, Kim JH, Kim HY, Kim WC. Comparison and evaluation of marginal and internal gaps in cobalt-chromium alloy copings fabricated using subtractive and additive manufacturing. *Journal of prosthodontic research*. 2018;62(1):56-64. <https://doi.org/10.1016/j.jprr.2017.05.008>
 10. Uzgur R, Ercan E, Uzgur Z, Çolak H, Yalçın M, Özcan M. Cement Thickness of Inlay Restorations Made of Lithium Disilicate, Polymer-Infiltrated Ceramic and Nano-Ceramic CAD/CAM Materials Evaluated Using 3D X-Ray Micro-Computed Tomography. *Journal of prosthodontics : official journal of the American College of Prosthodontists*. 2018;27(5):456-60. <https://doi.org/10.1111/jopr.12521>
 11. Stavridakis MM, Kakaboura AI, Ardu S, Krejci I. Marginal and internal adaptation of bulk-filled Class I and Cuspal coverage direct resin composite restorations. *Operative dentistry*. 2007;32(5):515-23. <https://doi.org/10.2341/06-157>
 12. Dionysopoulos D, Papadopoulos C, Koliniotou-Koumpia E. The evaluation of various restoration techniques on internal adaptation of composites in class v cavities. *International journal of biomaterials*. 2014;2014:148057. <https://doi.org/10.1155/2014/148057>
 13. Sachs C, Groesser J, Stadelmann M, Schweiger J, Erdelt K, Beuer F. Full-arch prostheses from translucent zirconia: accuracy of fit. *Dental materials : official publication of the Academy of Dental Materials*. 2014;30(8):817-23. <https://doi.org/10.1016/j.dental.2014.05.001>
 14. Acquaviva P, Madini L, Nembrini E, Brazzoli S, Papacchini F, Cerutti FA. Marginal adaptation of new bulk fill composites: Microscopical evaluation. *Dental Materials*. 2014(30):e125. <https://doi.org/10.1016/j.dental.2014.08.259>
 15. Son K, Lee S, Kang SH, Park J, Lee KB, Jeon M, et al. A Comparison Study of Marginal and Internal Fit Assessment Methods for Fixed Dental Prostheses. *Journal of clinical medicine*. 2019;8(6). <https://doi.org/10.3390/jcm8060785>
 16. Rajan BN, Jayaraman S, Kandhasamy B, Rajakumar I. Evaluation of marginal fit and internal adaptation of zirconia copings fabricated by two CAD - CAM systems: An in vitro study. *Journal of Indian Prosthodontic Society*. 2015;15(2):173-8. <https://doi.org/10.4103/0972-4052.159970>
 17. Park JY, Bae SY, Lee JJ, Kim JH, Kim HY, Kim WC. Evaluation of the marginal and internal gaps of three different dental prostheses: comparison of the silicone replica technique and three-dimensional superimposition analysis. *The journal of advanced prosthodontics*. 2017;9(3):159-69. <https://doi.org/10.4047/jap.2017.9.3.159>
 18. Han SH, Sadr A, Tagami J, Park SH. Non-destructive evaluation of an internal adaptation of resin composite restoration with swept-source optical coherence tomography and micro-CT. *Dental materials : official publication of the Academy of Dental Materials*. 2016;32(1):e1-7. <https://doi.org/10.1016/j.dental.2015.10.009>
 19. Schriwer C, Skjold A, Gjerdet NR, Øilo M. Monolithic zirconia dental crowns. Internal fit, margin quality, fracture mode and load at fracture. *Dental materials : official publication of the Academy of Dental Materials*. 2017;33(9):1012-20. <https://doi.org/10.1016/j.dental.2017.06.009>
 20. Homsy FR, Özcan M, Khoury M, Majzoub ZAK. Marginal and internal fit of pressed lithium disilicate inlays fabricated with milling, 3D printing, and conventional technologies. *The Journal of prosthetic dentistry*. 2018;119(5):783-90. <https://doi.org/10.1016/j.prosdent.2017.07.025>
 21. Falahchai M, Babae Hemmati Y, Neshandar Asli H, Emadi I. Marginal gap of monolithic zirconia endocrowns fabricated by using digital scanning and conventional impressions. *The Journal of prosthetic dentistry*. 2021;125(2):325.e1-.e5. <https://doi.org/10.1016/j.prosdent.2020.05.042>
 22. Peng CC, Chung KH, Ramos V, Jr. Assessment of the Adaptation of Interim Crowns using Different Measurement Techniques. *Journal of prosthodontics : official journal of the American College of Prosthodontists*. 2020;29(1):87-93. <https://doi.org/10.1111/jopr.13122>
 23. Falahchai M, Rahimabadi S, Khabazkar G,

- Babae Hemmati Y, Neshandar Asli H. Marginal and internal fit and fracture resistance of three-unit provisional restorations fabricated by additive, subtractive, and conventional methods. *Clinical and experimental dental research*. 2022;1-9.<https://doi.org/10.1002/cre2.637>
24. Boitelle P, Tapie L, Mawussi B, Fromentin O. Evaluation of the marginal fit of CAD-CAM zirconia copings: Comparison of 2D and 3D measurement methods. *The Journal of prosthetic dentistry*. 2018;119(1):75-81.<https://doi.org/10.1016/j.prosdent.2017.01.026>
25. Alharbi N, Alharbi S, Cuijpers V, Osman RB, Wismeijer D. Three-dimensional evaluation of marginal and internal fit of 3D-printed interim restorations fabricated on different finish line designs. *Journal of prosthodontic research*. 2018;62(2):218-26.<https://doi.org/10.1016/j.jpor.2017.09.002>
26. Ha SJ, Cho JH. Comparison of the fit accuracy of zirconia-based prostheses generated by two CAD/CAM systems. *The journal of advanced prosthodontics*. 2016;8(6):439-48.<https://doi.org/10.4047/jap.2016.8.6.439>
27. Falk A, Vult von Steyern P, Fransson H, Thorén MM. Reliability of the impression replica technique. *The International journal of prosthodontics*. 2015;28(2):179-80.<https://doi.org/10.11607/ijp.4132>
28. Groten M, Axmann D, Pröbster L, Weber H. Determination of the minimum number of marginal gap measurements required for practical in-vitro testing. *The Journal of prosthetic dentistry*. 2000;83(1):40-9.[https://doi.org/10.1016/S0022-3913\(00\)70087-4](https://doi.org/10.1016/S0022-3913(00)70087-4)
29. Son K, Lee K-B. Marginal and Internal Fit of Ceramic Prostheses Fabricated from Different Chairside CAD/CAM Systems: An In Vitro Study. *Applied Sciences*. 2021;11(2):857.<https://doi.org/10.3390/app11020857>
30. Holst S, Karl M, Wichmann M, Matta RE. A new triple-scan protocol for 3D fit assessment of dental restorations. *Quintessence international (Berlin, Germany : 1985)*. 2011;42(8):651-7.<https://doi.org/10.1177/1758736012452181>
31. Senawongse P, Pongprueksa P, Harnirattisai C, Sumi Y, Otsuki M, Shimada Y, et al. Non-destructive assessment of cavity wall adaptation of class V composite restoration using swept-source optical coherence tomography. *Dental materials journal*. 2011;30(4):517-22.<https://doi.org/10.4012/dmj.2011-061>
32. Haak R, Siegner J, Ziebolz D, Blunck U, Fischer S, Hajtó J, et al. OCT evaluation of the internal adaptation of ceramic veneers depending on preparation design and ceramic thickness. *Dental materials : official publication of the Academy of Dental Materials*. 2021;37(3):423-31.<https://doi.org/10.1016/j.dental.2020.11.021>
33. Contrepolis M, Soenen A, Bartala M, Laviolle O. Marginal adaptation of ceramic crowns: a systematic review. *The Journal of prosthetic dentistry*. 2013;110(6):447-54.e10.<https://doi.org/10.1016/j.prosdent.2013.08.003>
34. Bayrak A, Akat B, Ocak M, Kılıçarslan MA, Özcan M. Micro-Computed Tomography Analysis of Fit of Ceramic Inlays Produced with Different CAD Software Programs. *European Journal of Prosthodontics and Restorative Dentistry (2020)*. 2020; 28:1-6
35. Topkara C, Keleş A. Examining the adaptation of modified endocrowns prepared with CAD-CAM in maxillary and mandibular molars: A microcomputed tomography study. *The Journal of prosthetic dentistry*. 2021.<https://doi.org/10.1016/j.prosdent.2020.12.003>
36. Ashiry E, Alamoudi N, Farsi N, Tuwirqi A, Attar M, Alag H, et al. The Use of Micro-Computed Tomography for Evaluation of Internal Adaptation of Dental Restorative Materials in Primary Molars: An In-Vitro Study. 2019:129-37.
37. Ashy LM, Marghalani H. Internal and Marginal Adaptation of Adhesive Resin Cements Used for Luting Inlay Restorations: An In Vitro Micro-CT Study. *Materials (Basel, Switzerland)*. 2022;15(17).<https://doi.org/10.3390/ma15176161>
38. Erpaçal B, Adıgüzel Ö, Cangül S. The use of micro-computed tomography in dental applications. *International Dental Research*. 2019;9(2):78-91.<https://doi.org/10.5577/intdentres.2019.vol9.no2.7>
39. Ghavami-Lahiji M, Davaloo RT, Tajziehchi G, Shams P. Micro-computed tomography in preventive and restorative dental research: A review. *Imaging science in dentistry*. 2021;51(4):341-50.<https://doi.org/10.5624/isd.20210087>
40. Campioni I, Pecci R, Bedini R. Ten Years of Micro-CT in Dentistry and Maxillofacial Surgery: A Literature Overview. *Applied Sciences*. 2020;10(12):4328.<https://doi.org/10.3390/app10124328>
41. Sarda AS, Bedia SV. Influence of manufacturing technique on marginal fit of cobalt chromium restorations: An in-vitro Study. *Indian journal of dental research : official publication of Indian Society for Dental Research*. 2021;32(4):495-9.https://doi.org/10.4103/ijdr.IJDR_1075_20
42. Özal Ç, Ulusoy M. In-vitro evaluation of marginal and internal fit of 3-unit monolithic zirconia restorations fabricated using digital scanning technologies. *The journal of advanced prosthodontics*. 2021;13(6):373-84.<https://doi.org/10.4047/jap.2021.13.6.373>
43. Gautam N, Khajuria RR, Ahmed R, Sharma S, Hasan S, Hasan S. A Comparative Evaluation of Marginal Accuracy of Co-Cr Metal Copings Fabricated Using Traditional Casting Techniques and Metal Laser Sintering. *International journal of clinical pediatric dentistry*. 2021;14(1):128-32.<https://doi.org/10.5005/jp-journals-10005-1888>
44. Mansour FK, Ibrahim RM, Mansour H, Hamdy AM. Assessment of internal fit and micro leakage of conventionally fabricated ceramometallic restoration versus CAD wax and press veneering (in-vitro study). *BDJ open*. 2021;7(1):17.<https://doi.org/10.1038/s41405-021-00072-7>