

ResearchPaper: Comparing the Translucency of several enamel and universal- shade composite resins



Farideh Darabi¹, Maryam Tavangar², Reza Tayefeh Davaloo¹, Maryam Ghamgosar¹, Fateme Moosazade Hassan Kiadeh², Aref Khosravian³

¹Associate professor, Dental Sciences Research Center, Department. of Operative Dentistry, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran

²Assistant professor, Dental Sciences Research Center, Department of Operative Dentistry, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran

³Graduate Student, School of Dentistry, Tehran, Iran



Citation Darabi F, Tavangar M, Tayefeh Davaloo R, Ghamgosar M, Moosazade Hassan Kiadeh F, Khosravian A. Comparing the Translucency of several enamel and universal- shade composite resins. Journal of Dentomaxillofacial Radiology, Pathology and Surgery. 2023; 12(3):1-6.

 <http://dx.doi.org/10.32592/3dj.12.3.1>

ABSTRACT



Article info:

Received: 05 Aug 2023

Accepted: 22 Oct 2023

Available Online: 29 Oct 2023

Introduction: Translucency is one of the important optical properties of tooth color materials and it is greatly affected by the thickness of material. This study concerns comparing the translucency parameter (TP) of five different composite resins in different thicknesses.

Materials and Methods: Five brands of composite resins; Gradia (GC), Crystalline (Confidential) Vit-l-escence (Ultradent) in A2, and Herculite XRV (Kerr), Opallis (FGM) in enamel A2 (EA2) shades were selected to enroll the study. Color coordinates of each composite were determined at 0.5, 1, and 1.5 mm thicknesses on a white backing, the backing of material itself and a black backing were calculated by using a spectrophotometer to evaluate the translucency parameter (TP) of the study materials. The masking ability was also calculated from the specimens on the material itself and on black backing. The values under 2 were estimated as imperceptible. One-way ANOVA, T-test and Tukey HSD were employed for statistical analysis.

Results: Opallis (EA2) showed the less TP values in all thicknesses in comparison to the other materials ($p < 0.05$) but there was no statistically significant difference between TP values of Gradia and Opallis in 1.5 and 0.5 mm-thick. The masking ability values recorded for all specimens at different thicknesses, were in the range of perceptible.

Conclusion: In this study, translucency of Opallis (EA2) and Gradia(A2) was less than the other enamel /universal shade composites. For this reason, it would be concluded that if the restoration thickness is ≤ 1.5 mm, these enamel/universal shade composite resins cannot mask the black background color.

Keywords:

Translucency
Composite Resins
Perceptual Masking
Dental Enamel

* Corresponding Authors:

Maryam Tavangar

Address: Associate professor, Dental Sciences Research Center, Dept. of Operative Dentistry, School of Dentistry, Guilan University of Medical Sciences, Rasht, Iran

Tel: +981333486418

E-mail: Marjan_tavangar@yahoo.com

1. Introduction

It is widely argued that duplicating color properties and characteristics of the tooth structure by dental materials are considered as great challenging responsibilities in dentistry. (1,2)

In some clinical situations, for example, in order to restore the cavities with backing of natural dentin or apply composite veneers of the teeth with no dark discoloration, we should choose enamel or universal shade of composite resins. More exactly, translucency is one of the most important optical properties of tooth color materials. (1-3) Moreover, hue, chroma and value are three dimensions of color and value which are profoundly relevant to translucency. (4-6) To confirm the given claims, a direct correlation has been shown between the translucency of composite resins and chameleon effect. (7)

It is also worth mentioning that the translucency degree of enamel -shade composite resins can change the color perception of the underlying natural dentin or dentin-shade resins. (8)

There are a lot of studies about the translucency of composite resins and the effective factors on it. Some of the factors affecting the composite resins translucency include: shade (5,6), thickness (4,7), size and content of fillers (9,10), matrix composition (11,12) and refractive index of matrix and filler particles. (13)

According to previous studies, different brands of composite resin in the same shade category (enamel, dentin, body, opaque) and thickness, showed significant differences in translucency. (5,14,15)

In the study directed by Balci et al. (16) the translucency parameters of seven anterior composite resins were different from each other and there was not any relationship between different classes of materials.

It is necessary to point out that the translucency of enamel color composite resins is greatly influenced by the material thickness. (4-6) Therefore, it is necessary to evaluate and compare the translucency of the available composite resins in our market.

In this study, comparing the translucency parameters (TP) of several available composite resins in different thicknesses is of concern not to mention evaluating their abilities to mask black background color is also of importance to be studied.

On the basis of the purpose of the study, the following two hypotheses are supposed to be tested:

H1: There are no significant differences between the TP values of each composite resin at different thicknesses or

the same thicknesses of different composite resins.

H2: None of the composite resins can mask black background.

2. Materials and Methods

Five brands of resin composites; Gradia (GC; Tokyo, Japan), Vit-l-escence (Ultradent; South Jordan, USA), Crystalline (Confi-dental; Louisville, USA) in A2 shade and Herculite XRV (Kerr; Scafati, Salerno, Italy), Opallis (FGM, Brazil) in enamel A2(EA2) shade were enrolled in this study. To be more precise, stainless-steel split plates in 0.5, 1, 1.5 mm thicknesses and with a hole of 18 mm in diameter were used as the molds to produce standardized specimens. At first, each mold was filled with resin composite material and covered with clear celluloid strips on the top and the bottom of the hole.

Next, the metal plate was pressed between two glass-slides for 10 seconds. Then, the glass slides were removed. After that, the specimens were light cured for 40 seconds in eight overlapping areas with two light-curing units (Litex 680; Dentamerica, USA) simultaneously. The light intensity was 400m W/cm² and the output of the light was checked with a radiometer. Finally, five specimens from each material thickness were made and after their storage in distilled water for 24 hours, the specimens were polished with a wet 1500-grit silicon carbide paper (3M ESPE; St. Paul, USA) on both sides.

It is worth mentioning that the CIE L*a*b*(CIELAB) technique was employed in the present study. This technique is introduced by the International Commission on Illumination (French Commission Internationale de l'éclairage (CIE) which is an organization that establishes the standard values used worldwide to measure color. The values used by CIE are called L*, a* and b* and the color measurement method is called CIE L*a*b* (CIELAB). L* is lightness, where 100 is completely white and 0 is completely black, and a* and b* are red-green and yellow-blue chromatic coordinates, respectively. A positive a* or b* value represents a red or yellow shade respectively. (4-8)

In the current study, three backgrounds; white tile (L*=94.32, a*=-0.46, b*=1.26), black tile (L*=0.06, a*=-0.01, b*=0.01), and resin itself were used to determine the translucency parameter (TP) (between black and white backgrounds), and to mimic a black oral cavity (between black and resin backgrounds).

To determine the CIELAB values of each specimen with each background, color measurements were performed by employing spectrophotometer (Color-Eye 7000 A; Gretag Macbeth, USA). Furthermore, optical contact was achieved by using an optical fluid (refractive index =1.5) between the composite resin specimen and background.

Additionally, light source illumination was matched with the average daylight (D65). The last but not the least, the translucency parameter of the material at various thicknesses was calculated using the following equation:

$$TP = [(L^*W - L^*B)^2 + (a^*W - a^*B)^2 + (b^*W - b^*B)^2]^{1/2}$$

The subscript "W" and "B" refers to the CIELAB values for each specimen on white backing and black backing, respectively. The ability of each material to mask dark oral cavity was determined by calculating the ΔE^* of the specimens between the material itself and on black backing using the following equation:

$$\Delta E = \{(\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2\}^{1/2}$$

A smaller ΔE^* indicates that the specimen is less sensitive to (as in better able to mask) the black back ground color. The ΔE^* value was assessed for each thickness and a value of $\Delta E^* \leq 2$ was considered clinically imperceptible regarding the method used by some previous studies. (5,15)

To evaluate any statistical changes in the TP of different thicknesses in each composite, one-way analysis of variance (ANOVA) was conducted. To compare the TP

between different materials at the same thicknesses, Tukey HSD test was performed and it was set at the 0.05 level of significance.

3. Results

The median values L^* , a^* and b^* of each composite at three thicknesses and backgrounds and also the values of ΔE^* for each material at different thicknesses have been specified in Table 1.

One-way ANOVA test showed significant differences in TP values in different thicknesses (0.5, 1, 1.5) of each material.

The comparison of the TP of different composite resins with the same thickness has been illustrated in Table 2.

In all thicknesses (0.5, 1, 1.5), Opallis showed the less TP values in comparison to the other materials ($p < 0.05$) but there was no statistically significant difference between TP values of Gradia and Opallis in 1.5 and 0.5 mm-thick.

The ΔE^* values recorded for all composite resins were higher than 2. It means that all composites at 0.5, 1 and 1.5 - mm- thicknesses may not mask the black background.

Table 1. Mean (SD) of CIE L^* , a^* , b^* and ΔE values in 0.5, 1 and 1.5 mm thickness of resin composites over backgrounds

Material	Shade	Thickness	L^* (SD)			a^* (SD)			b^* (SD)			ΔE
			White	Material Itself	black	White	Material Itself	black	white	Material Itself	black	
Gradia direct	A2	0.5	68.45(2.36)	67.21(2.40)	63.05(2.34)	1.71(0.09)	1.31(0.1)	0.92(0.04)	16.52(0.3)	15.89(0.35)	13.41(0.3)	4.29(0.16)
		1	69.4(1.08)	66.43(0.83)	64.58(0.38)	2.84(0.19)	2.24(0.2)	1.04(0.06)	15.82(0.04)	15.28(0.39)	12.45(0.37)	3.69(0.32)
		1.5	74.30(0.13)	73.89(0.21)	71.42(0.37)	3.87(0.06)	2.20(0.008)	1.28(0.008)	13.28(0.14)	12.20(0.03)	10.99(0.04)	2.91(0.2)
Herculite	EA2	0.5	63.46(0.36)	63.03(0.36)	58.19(0.25)	3.03(0.27)	2.16(0.27)	1.44(0.33)	15.62(0.32)	14.6(0.32)	11.75(0.37)	5.66(0.06)
		1	69.81(0.38)	67.21(0.3)	63.4(0.21)	3.55(0.22)	2.46(0.26)	1.62(0.34)	10.52(0.5)	10.41(0.43)	7.79(0.26)	4.7(0.16)
		1.5	65.97(0.81)	65.58(1.72)	61.83(0.31)	3.40(0.14)	2.78(0.05)	1.89(0.04)	11.69(0.2)	10.09(0.08)	9.29(0.31)	3.95(1.76)
Crystalfill	A2	0.5	7.39(0.36)	76.6(0.36)	71.56(0.4)	2.72(0.07)	2.13(0.05)	3.3(0.11)	10.11(0.29)	9.45(0.83)	7.98(0.35)	4.27(0.17)
		1	68.87(0.28)	66.38(0.37)	61.66(0.38)	2.49(0.35)	2.6(0.45)	3.45(0.35)	11.75(0.44)	9.69(0.26)	8.01(0.24)	5.08(0.1)
		1.5	68.22(0.15)	66.94(0.19)	63.76(0.16)	1.74(0.09)	1.06(0.06)	0.75(0.1)	14.89(0.11)	12.93(0.22)	11.69(0.13)	3.42(0.08)
Vitalnessence	A2	0.5	77.41(0.27)	74.43(0.26)	70.24(0.31)	3.14(0.1)	3(0.16)	2.38(0.73)	8.14(0.16)	7.15(0.19)	6.98(0.12)	4.85(0.13)
		1	79.24(0.4)	78.12(0.38)	75.42(0.41)	1.73(0.3)	1.84(1.4)	2.27(1.25)	7.86(0.37)	4.47(0.37)	3.07(0.31)	4.97(0.09)
		1.5	69.72(0.27)	67.91(0.22)	64.22(0.19)	2.47(0.36)	1.74(0.62)	1.05(0.04)	8.48(0.2)	7.79(0.03)	6.94(0.06)	3.88(0.07)
Opallis	EA2	0.5	21.12(0.27)	80.38(0.3)	76.16(0.15)	6.02(0.04)	5.44(0.06)	4.95(0.01)	21.12(0.27)	19.78(0.14)	19.75(0.44)	4.27(0.17)
		1	72.68(0.32)	70.54(0.43)	67.46(0.46)	1.46(0.46)	1.1(0.39)	0.62(0.38)	16.10(0.35)	16.13(0.33)	12.25(0.41)	3.74(0.28)
		1.5	72.54(0.1)	70.86(0.08)	69.47(0.15)	1.07(0.07)	1.39(0.14)	0.39(0.57)	17.65(0.16)	16.51(0.19)	14.72(0.26)	2.53(0.1)

Material	Shade	Thickness	L* (SD)			a* (SD)			b* (SD)			ΔE
			White	Material itself	black	White	Material itself	black	white	Material itself	black	
Gradia direct	A2	0.5	68.45(2.36)	67.21(2.40)	63.05(2.34)	1.71(0.09)	1.31(0.1)	0.92(0.04)	16.52(0.3)	15.89(0.35)	13.41(0.3)	4.29(0.16)
		1	69.4(1.08)	66.43(0.83)	64.58(0.38)	2.84(0.19)	2.24(0.2)	1.04(0.06)	15.82(0.04)	15.28(0.39)	12.45(0.37)	3.69(0.32)
		1.5	74.30(0.13)	73.89(0.21)	71.42(0.37)	3.87(0.06)	2.20(0.008)	1.28(0.008)	13.28(0.14)	12.20(0.03)	10.99(0.04)	2.91(0.2)
Herculite	EA2	0.5	63.46(0.36)	63.03(0.36)	58.19(0.25)	3.03(0.27)	2.16(0.27)	1.44(0.33)	15.62(0.32)	14.6(0.32)	11.75(0.37)	5.66(0.06)
		1	69.81(0.38)	67.21(0.3)	63.4(0.21)	3.55(0.22)	2.46(0.26)	1.62(0.34)	10.52(0.5)	10.41(0.43)	7.79(0.26)	4.7(0.16)
		1.5	65.97(0.81)	65.58(1.72)	61.83(0.31)	3.40(0.14)	2.78(0.05)	1.89(0.04)	11.69(0.2)	10.09(0.08)	9.29(0.31)	3.95(1.76)
Crystalline	A2	0.5	7.39(0.36)	76.6(0.36)	71.56(0.4)	2.72(0.07)	2.13(0.05)	3.3(0.11)	10.11(0.29)	9.45(0.83)	7.98(0.35)	4.27(0.17)
		1	68.87(0.28)	66.38(0.37)	61.66(0.38)	2.49(0.35)	2.6(0.45)	3.45(0.35)	11.75(0.44)	9.69(0.26)	8.01(0.24)	5.08(0.1)
		1.5	68.22(0.15)	66.94(0.19)	63.76(0.16)	1.74(0.09)	1.06(0.06)	0.75(0.1)	14.89(0.11)	12.93(0.22)	11.69(0.13)	3.42(0.08)
Vitaescence	A2	0.5	77.41(0.27)	74.43(0.26)	70.24(0.31)	3.14(0.1)	3(0.16)	2.38(0.73)	8.14(0.16)	7.15(0.19)	6.98(0.12)	4.85(0.13)
		1	79.24(0.4)	78.12(0.38)	75.42(0.41)	1.73(0.3)	1.84(1.4)	2.27(1.25)	7.86(0.37)	4.47(0.37)	3.07(0.31)	4.97(0.09)
		1.5	69.72(0.27)	67.91(0.22)	64.22(0.19)	2.47(0.36)	1.74(0.62)	1.05(0.04)	8.48(0.2)	7.79(0.03)	6.94(0.06)	3.88(0.07)
Opallis	EA2	0.5	21.12(0.27)	80.38(0.3)	76.16(0.15)	6.02(0.04)	5.44(0.06)	4.95(0.01)	21.12(0.27)	19.78(0.14)	19.75(0.44)	4.27(0.17)
		1	72.68(0.32)	70.54(0.43)	67.46(0.46)	1.46(0.46)	1.1(0.39)	0.62(0.38)	16.10(0.35)	16.13(0.33)	12.25(0.41)	3.74(0.28)
		1.5	72.54(0.1)	70.86(0.08)	69.47(0.15)	1.07(0.07)	1.39(0.14)	0.39(0.57)	17.65(0.16)	16.51(0.19)	14.72(0.26)	2.53(0.1)

L*lightness; a*, redness (positive +a*) or greenness (negative -a*); b*, yellowness (positive + b*) or blueness(negative - b*).
EA2, Enamel A2; A2, universal A2

Table 2. Mean (SD) TP values of different materials

Material	Color	TP (SD) Thickness		
		0.5	1	1.5
Gradia Direct	A2	6.27(0.03) ^b	6.18(0.42) ^a	4.56(0.1) ^b
Herculite	EA2	7.43(0.22) ^a	6.72(0.03) ^a	5.02(0.47) ^a
Crystalline	A2	7.51(1.07) ^a	6.23(0.17) ^a	5.58(0.07) ^a
Vitaescence	A2	7.33(0.09) ^a	6.2(0.03) ^a	5.89(0.02) ^a
Opallis	EA2	5.25(0.28) ^b	5.01(0.16) ^b	4.32(0.07) ^b

Note: Different superscript letters in each column show a significant difference among the investigate materials

4. Discussion

It can be seen from the above analysis that information about the translucency of the composite resins in different thicknesses helps clinicians in choosing the appropriate and accurate material in different clinical situations. (17) The result of the present study revealed significant differences of translucency between different thicknesses of the same composite. However, regardless of shade category, some of composite resins showed no significant difference in translucency parameter with the same thicknesses. Consequently, the first null hypothesis was partially rejected.

These findings are consistent with the findings of the

other researchers who demonstrated that the thicker composite resins were less translucent. (3-5,18)

In our study EA2shade of opallis showed lower translucency than A2(universal) shade of Crystalline and Vitaescence at the same thicknesses. And also, translucency parameter of A2 shade of Vitaescence(which is recommended as substituted of dentin by its manufacturer) was similar to enamel EA2 shade of Herculite. These findings are in consistent with the other studies which showed there was no standard shade category among the manufactures. (14,18,19)

In our study, Tp values of Opallis and Gradia were lower than the others. That is to say, the most important

difference between the composite resins in our study is their matrix composition. In other words, the matrix of composite resins in this study, except Opallis and Gradia, were based on Bis-GMA. In addition, Opallis is a nanohybrid composite resin and its matrix contains Bis-GMA, Bis-EMA, UDMA, TEGDMA and matrix composition in Gradia which is UDMA-based. (20,21) Azzopardi et al. (11) reported that Bis-GMA containing resin were more translucent than UDMA- and TEGDMA-based composite resins. In a study by Pereira et al. (12), the UDMA-based materials showed the lowest TP value.

The ΔE^* values of different composites for masking the black background in this study showed a negative relationship with their thickness. This result is in agreement with previous studies. (14,15,17,22) The threshold for clinically acceptable color difference has been reported as $\Delta E^* \leq 2$ [4,15,23,24], $\Delta E^* \leq 2.7$ (25), $\Delta E^* \leq 3.3$ (26), $\Delta E^* \leq 3.7$ (27). It should be noted that the clinically acceptable threshold of ≤ 2 was used in this study. Based on this, the values of ΔE^* between 0 and 2 are imperceptible and values of ΔE^* in the range of 2 to 3 are just perceptible, 3 to 8 are moderately perceptible and values above 8 are markedly perceptible. (23) According to this category, none of the composite resins in our study could completely mask the black background, so the second hypothesis was accepted. Therefore, using them to restore a through-and-through class III or IV cavity would probably lead to a show-through appearance.

Among the composite resins in our study, Opallis and Gradia at 1.5 mm thicknesses showed the less TP value and a $3 > \Delta E^* > 2$, making them as a material of choice to mask slight tooth discoloration. However, further investigations are needed using different background colors for example C2, C3, C 4.

In natural dentition, translucency value varies among individuals, tooth type and age. (8) To reproduce the optical properties of natural teeth, each part of the tooth must be replaced by the material with properties similar to those of tooth. Lee (2) stated that translucency of human teeth should be the reference in the translucency assessment of restorative materials. About the translucency of human teeth, limited reports are available. In the study conducted by Ryan et al. (14), the mean TP value of human enamel at 2 mm thicknesses was $11.6(\pm 0.3)$. Yu et al. (28) reported the translucency parameter of 1- mm -thick human enamel and dentin 18.7 and 16.4, respectively. A recent study also reported the mean in vivo TP of vital incisor enamel at 2 mm thicknesses, $10.1(\pm 3.6)$. (29) However, in our study, TP values of 1- mm -thick composite resins ranged from 4.32(SD 0.07) to 5.89(SD 0.02) which was much lower than those reported for human enamel at the same

thickness. In consistent with our results, in a study by Ryan et al. (14) enamel – shade composite resins obtained lower TP values in comparison to human enamel. Nevertheless, the data obtained from different studies cannot be directly compared due to the differences in experimental conditions, methods and materials. (1)

To recapitulate, more investigations are needed to compare TP values of composite resins, human enamel and dentin at the same conditions.

However, the result of this in vitro study should be cautiously extrapolated to clinical situations because of some other factors such as surface texture and degree of polishing which may affect the optical properties of the restoration.

5. Conclusion

Within the limitations of this study such as low masking ability of these composite resins and in through-and-through class III and IV restorations, dentin/opaque shade composite resins had better be used as a backing in a layering technique. Moreover, among the studied composite resins, Opallis and Gradia showed lower translucency, subsequently, they can be used to cover minor tooth discoloration or restore an area with less translucency.

Ethical Considerations

Compliance with ethical guidelines

Not applicable.

Funding

None.

Authors' contributions

Farideh Darabi: Conceptualization, Methodology, Writing - Review & Editing Maryam Tavangar: Resources, Investigation, Visualization Vanya Rasaie: Methodology, Visualization Reza Tayefeh Davaloo: Writing - Original Draft, Data Curation Maryam Ghamgosar: Funding acquisition, Project administration, Supervision Fateme Moosazadeh Hassan Kiadeh: Writing - Review & Editing Resources Aref Khosravian: Writing - Review & Editing Investigation.

Conflict of Interests

The authors declare no conflict of interest.

Availability of data and material

The datasets used and/or analyzed during the current study are available from the corresponding author on reasonable request.

Acknowledgments

None.

References

- Johnston WM. Review of translucency determinations and applications to dental materials. *J Esthet Restor Dent*. 2014; 26(4):217-23. [DOI: 10.1111/jerd.12112] [PMID]
- Lee YK. Translucency of human teeth and dental restorative materials and its clinical relevance. *Journal of Biomedical Optics*. 2015;20(4):045002. [DOI: 10.1117/1.JBO.20.4.045002]
- Arimoto A, Nakajima M, Hosaka K, Nishimura K, Ikeda M, Foxton RM, Tagami J. Translucency, opalescence and light transmission characteristics of light-cured resin composites. *Dental Materials*. 2010;26(11):1090-7. [DOI: 10.1016/j.dental.2010.07.009]
- Schmeling M, DE ANDRADA MA, Maia HP, De Araujo EM. Translucency of value resin composites used to replace enamel in stratified composite restoration techniques. *Journal of Esthetic and Restorative Dentistry*. 2012;24(1):53-8. [DOI: 10.1111/j.1708-8240.2011.00419.x]
- Kim D, Park SH. Color and translucency of resin-based composites: comparison of a-shade specimens within various product lines. *Oper Dent*. 2018;43(6):642-55. [DOI: 10.2341/17-228-L]
- Naeimi Akbar H, Moharamzadeh K, Wood DJ, Van Noort R. Relationship between color and translucency of multishaded dental composite resins. *International journal of dentistry*. 2012;2012. [DOI: 10.1155/2012/708032]
- Ota M, Ando S, Endo H, Ogura Y, Miyazaki M, Hosoya Y. Influence of refractive index on optical parameters of experimental resin composites. *Acta Odontologica Scandinavica*. 2012;70(5):362-7. [DOI: 10.3109/00016357.2011.600724]
- Villarroel M, Fahl N, De Sousa AM, de Oliveira OB. Direct esthetic restorations based on translucency and opacity of composite resins. *Journal of Esthetic and Restorative Dentistry*. 2011;23(2):73-87. [DOI: 10.1111/j.1708-8240.2010.00393.x]
- Maia RR, Oliveira D, D'antonio T, Qian F, Skiff F. Comparison of light-transmittance in dental tissues and dental composite restorations using incremental layering build-up with varying enamel resin layer thickness. *Restor Dent Endod*. 2018;43(2). [DOI: 0.5395/rde.2018.43.e22]
- Lim YK, Lee YK, Lim BS, Rhee SH, Yang HC. Influence of filler distribution on the color parameters of experimental resin composites. *Dental Materials*. 2008;24(1):67-73. [DOI: 10.1016/j.dental.2007.02.007]
- Azzopardi N, Moharamzadeh K, Wood DJ, Martin N, van Noort R. Effect of resin matrix composition on the translucency of experimental dental composite resins. *Dental Materials*. 2009;25(12):1564-8. [DOI: 10.1016/j.dental.2009.07.011]
- Pereira LD, Neto MP, Pereira RG, Schneider LF. Influence of resin matrix on the rheology, translucency, and curing potential of experimental flowable composites for bulk-fill applications. *Dental Materials*. 2021;37(6):1046-53. [DOI: 10.1016/j.dental.2021.03.003]
- Oivanen M, Keulemans F, Garoushi S, Vallittu PK, Lassila L. The effect of refractive index of fillers and polymer matrix on translucency and color matching of dental resin composite. *Biomaterial investigations in dentistry*. 2021;8(1):48-53. [DOI: 10.1080/26415275.2021.1906879]
- Ryan EA, Tam LE, McComb D. Comparative translucency of esthetic composite resin restorative materials. *J Can Dent Assoc*. 2010;76:a84. [PMID]
- Darabi F, Radafshar G, Tavangar M, Davaloo R, Khosravian A, Mirfarhadi N. Translucency and masking ability of various composite resins at different thicknesses. *J Dent*. 2014;15(3):117. [PMID] [PMCID]
- Balci M, Ergucu Z, Çelik EU, Turkun LS. Comparison between translucencies of anterior resin composites and natural dental tissues. *Color Research & Application*. 2021;46(3):635-44. [DOI: 10.1002/col.22645]
- Perez BG, Gaidarji B, Righes DZ, Pecho OE, Pereira GK, Durand LB. Masking ability of resin composites: A scoping review. *Journal of Esthetic and Restorative Dentistry*. 2023;35(2):333-44. [DOI: 10.1111/jerd.12976]
- Kamishima N, Ikeda T, Sano H. Color and translucency of resin composites for layering techniques. *Dental materials journal*. 2005;24(3):428-32. [DOI: 10.4012/dmj.24.428]
- Ikeda T, Sidhu SK, Omata Y, Fujita M, Sano H. Colour and translucency of opaque-shades and body-shades of resin composites. *European Journal of Oral Sciences*. 2005;113(2):170-3. [DOI: 10.1111/j.1600-0722.2005.00205.x]
- Opallis composite resin. 2024. [Link]
- Gradia direct composite resin. 2023. [Link]
- Valizadeh-Haghi H, Molaee S, Kamran A, Davoodzadeh S. Masking ability of bleach shade composite resins in different thicknesses. *International Journal of Dentistry*. 2022;2022. [DOI: 10.1155/2022/7479299]
- Gross MD, Moser JB. A colorimetric study of coffee and tea staining of four composite resins. *Journal of Oral Rehabilitation*. 1977;4(4):311-22. [DOI: 10.1111/j.1365-2842.1977.tb00997.x]
- O'brien WJ, Groh CL, Boenke KM. A new, small-color-difference equation for dental shades. *Journal of dental research*. 1990;69(11):1762-4. [DOI: 10.1177/00220345900690111001]
- Ghorab SM, Atya HA. Effect of thickness on translucency and masking ability of a recently developed single-shade resin composite with enhanced opacity: An in vitro comparative study. *Future*. 2021;7(2):130-5. [Link]
- Ruyter IE, Nilner K, Möller BJ. Color stability of dental composite resin materials for crown and bridge veneers. *Dental Materials*. 1987;3(5):246-51. [DOI: 10.1016/S0109-5641(87)80081-7]
- Johnston WM, Kao E. Assessment of appearance match by visual observation and clinical colorimetry. *Journal of dental research*. 1989;68(5):819-22. [DOI: 10.1177/00220345890680051301]
- Yu B, Ahn JS, Lee YK. Measurement of translucency of tooth enamel and dentin. *Acta Odontologica Scandinavica*. 2009;67(1): 57-64. [DOI: 10.1080/00016350802577818]
- Wee AG, Winkelmann DA, Gozalo DJ, Ito M, Johnston WM. Color and translucency of enamel in vital maxillary central incisors. *The Journal of Prosthetic Dentistry*. 2022. 1977; 4: 311-322. [DOI: 10.1016/j.prosdent.2022.01.010]